



# Comparative studies of fibres of woody species selected in relation to their paper-making potentials

## Estudios comparativos de fibras de especies de madera seleccionadas en relación con sus potenciales de hacer papel

Godswill C. Ajuziogu<sup>1</sup>, Eugene O. Ojua<sup>1\*</sup>, Ngozi E. Abu<sup>1</sup>, Christopher C. Onyeki<sup>1</sup>, Virginus O. Ayogu<sup>1</sup>,  
Anthony E. Nweze<sup>1</sup> and Solomon Nworie<sup>1</sup>

<sup>1</sup> University of Nigeria, Department of Plant Science  
and Biotechnology, Nsukka, Nigeria.

\* Corresponding author.  
eugene.ojua.pg78127@unn.edu.ng

### ABSTRACT

The wood fibre used by the paper industry originates primarily from forests. Apart from *Gmelina arborea*, there are other fast-growing plant species whose fibre characteristics are yet unknown. In order to relieve the pressure and demand on *G. arborea*, this work was aimed at characterizing and comparing the fibres of four tree species (*Parkia biglobosa*, *Arzadirachta indica*, *Alstonia boonei* and *Cassia siamea*) to *G. arborea*, with the intention of elucidating their suitability for the pulp and paper industry. The trunk wood samples used in this study were collected from the Botanical Garden of the University of Nigeria, Nsukka, while the study was conducted in the Plant Anatomy Laboratory in the Department of Plant Science and Biotechnology, University of Nigeria, Nsukka, Enugu State-Nigeria. The results showed that the mean fibre length ranged from 1.00 mm in *P. biglobosa* to 1.70 mm in *A. boonei*. The fibre lengths of *G. arborea* and *A. boonei* do not vary significantly ( $P < 0.05$ ). The Runkel ratio ranged from 0.624 to 3.227 across the species with *G. arborea* and *A. boonei* recording the lowest values. Conclusively, *A. boonei* is another pulp wood with good paper-making potential that could substitute the already known *G. arborea*.

KEYWORDS: *Alstonia boonei*; fibre; *Gmelina arborea*; Nigeria; papermaking; pulp wood.

### RESUMEN

Las fibras de la madera usadas en la industria del papel tienen su origen en los bosques. Además de *Gmelina arborea*, existen otras especies de rápido crecimiento, cuyas características de fibras aún son desconocidas. Con el fin de aligerar la presión y la demanda de *G. arborea*, este trabajo tuvo como objetivo caracterizar y comparar las fibras de cuatro especies (*Parkia biglobosa*, *Arzadirachta indica*, *Alstonia boonei* y *Cassia siamea*) con las de *G. arborea*, en cuanto a su idoneidad para la industria de la pulpa y el papel. Las muestras de madera utilizadas en este estudio fueron colectadas en el jardín botánico de la Universidad de Nigeria, Nsukka; el estudio se llevó a cabo en el Laboratorio de Anatomía de las Plantas en el Departamento de Ciencias de la Plantas y Biotecnología, Universidad de Nigeria, Nsukka, Enugu State-Nigeria. Los resultados mostraron que la longitud media de la fibra varió desde 1.00 mm en *P. biglobosa* hasta 1.70 mm en *A. boonei*. Las longitudes de las fibras de *G. arborea* y *A. boonei* no variaron significativamente ( $P < 0.5$ ). La relación de Runkel varió de 0.624 a 3.227 entre las especies, con *G. arborea* y *A. boonei* registrando los valores más bajos. Se concluyó que *A. boonei* es otra especie que proporciona pulpa con buen potencial para hacer papel, pudiendo sustituir a la ya conocida *G. arborea*.

PALABRAS CLAVE: *Alstonia boonei*; fibra; *Gmelina arborea*; Nigeria; fabricación de papel; pulpa de madera.

## INTRODUCTION

Paper as an end-user product has proven to be critical in driving most sensitive needs of mankind, remarkably in areas of security, education, sanitation, and communication (Ezeudu, Agunwamba, Ezeasor, & Madu, 2019). Paper is made from fibrous materials, whereby the most recent economical source of fibre is wood. The wood fibre used by the paper industry originates primarily from plantation forests (Ervasti, 2016). However, fibre raw material in paper production can be classified into two main pulp categories; virgin wood pulps produced from primary wood fibres and recycled fibre pulps generated from recycling of materials. Non-fiber materials such as annual plants, minerals and additives are in addition used as raw material in paper production (Ervasti, 2016).

One of the largest forest products imported into Nigeria is pulp and paper products. This was due to the stability experienced in the global pulp and paper market. Therefore, developing capacities of pulp and paper were not of necessity (Egbewole & Rotowa, 2017). However, due to the expansion of the global market, the market for pulp and paper began to increase. In order to make use of available raw materials and reduce foreign exchange expenditure, to protect local consumers from the high import prices, develop local industry to promote national industrial development aspirations and provide employment for its population, developing countries began to engage in pulp and paper manufacturing (Picornelli, 1984; Egbewole & Rotowa, 2017).

The term 'fibre' in anatomical sense refers to the sclerenchymatous fibres, which serve primarily as support to the plant. In an industrial sense, it includes sclerenchymatous fibres, tracheids and vessels (Anon, 2012; Hellgren, 2003). The quantity and properties of fibres, affect the suitability of tree species and their genetic entries as a raw material for mechanical wood processing and pulp and paper production (Peltola *et al.*, 2009). The pulp and

paper quality tend to relate closely to fibre dimensions with particular reference to tracheids and libriform fibres, as it is mainly on the basis of fibre dimensions that softwood pulp is in greater demand than hardwood pulp (Rydholm, 1967).

Researches had been carried out on *Gmelina arborea*, and have been found suitable for making low grade paper which has found tremendous usage in the newspaper and packaging industries (Chittenden & Rotibi, 1962; Ademiluyi & Okeke, 1979; Kpikpi & Olatunji, 1990; Ajuziogu, Ojua, & Aina, 2019). For this reason, the government of Nigeria in the 1960's established a pulping mill at Oku-Iboku in Akwa-Ibom State which processes *G. arborea* pulp for local consumption. Apart from *G. arborea*, there are other fast-growing plant species whose fibre characteristics are not yet known. In order to relieve the pressure and demand on *G. arborea*, there is the need to assess the paper-making potentials of these tree species.

## OBJECTIVES

The objective of this present study was to characterize and compare the fibres of four tree species – *P. biglobosa*, *A. indica*, *A. boonei* and *C. siamea* commonly found in the South-eastern part of Nigeria to *G. arborea*, with the intention to elucidating their suitability for the pulp and paper industry.

## MATERIALS AND METHODS

### Sample collection

The trunk wood samples used in this study were collected from the Botanic garden of the University of Nigeria, Nsukka. Ten samples were randomly collected at different positions within the breast height of each tree that was felled. The sampling was carried out using a chainsaw during a thinning exercise. The trees from where samples were collected were reliably identified based on their morphological and floral characteristics as described by Keay, Onochie and Stanfield (1964). The plant species and their families are given in table 1.



TABLE 1. Plant species and families.

<i>Plant Species</i>	<i>Family</i>
<i>Parkia biglobosa</i> (Jacq.) Bent	Mimosaceae
<i>Gmelina arborea</i> (Roxb.)	Verbenaceae
<i>Alstonia boonei</i> (Lam)	Apocynaceae
<i>Cassia siamea</i> Lam.	Caesalpinaceae
<i>Azadirachta indica</i> . A. Juss.	Meliaceae

### Maceration of wood sample

The study was conducted in the Plant Anatomy Laboratory in the Department of Plant Science and Biotechnology, University of Nigeria, Nsukka, Enugu State- Nigeria. The Schultze method of maceration as adopted by Kpikpi (1992) was used. This involved splitting the wood samples into small pieces, about the size of a matchstick, to expose large surface areas of contact between the wood and chemicals used, in order to facilitate the maceration process. A quantity of material was chipped such that enough pulp was obtained for evaluation. The samples from the different trees were placed separately into five long Borax test tubes that were well labelled. To each of these test tubes, 2 g Potassium chlorate (v) ( $KClO_3$ ) crystals and then 10 ml of concentrated Trioxonitrate (v) acid ( $HNO_3$ ) were added. The test tubes were then placed in a test tube rack and allowed to stand for about 30 minutes to enable the samples to react very well in the solution until they became softened and bleached. The Potassium trioxochlorate (v) acts as a powerful oxidizing agent capable of causing instant reaction with concentrated  $HNO_3$  to cause maceration. The maceration process was to dissolve the middle lamella which includes the lignin holding the plant cells together.

At the end of the reaction, excess solution was drained off and the softened pulp washed several times with tap water to prevent further reaction, while making sure no fibres were lost in the process. The washed fibres were then transferred into well-labeled specimen bottles and two drops of phenol and glycerine added to prevent moulding and remove air bubbles respectively. The wood fibres were stained with safranin to render the lignified wall more visible under the microscope.

### Measurement of fibre dimensions

Measurement of fibre dimensions was done using a compound microscope to which an eye-piece micrometer was fitted. The dimensions measured were the fibre length (L), fibre diameter (D); fibre cell wall thickness (C) and fibre lumen diameter (I). The measurements were taken at x400 magnification in determining the fibre cell wall thickness and lumen diameter, while the fibre length was taken at x100 magnification. The eye-piece micrometer was calibrated using a stage micrometer. Fifteen measurements of the fibre dimensions were taken, and derived fibre values- Runkel ratio (RR), Slenderness ratio (SR) and Coefficient of flexibility (CF), worked out as follows:

- Runkel ratio =  $2C/l$
- Coefficient of flexibility =  $l/D$
- Slenderness ratio =  $L/D$

Where

C = Cell wall thickness

l = Fibre lumen diameter

D = Fibre diameter

L = Fibre length

### RESULTS

The analysis of variance shows that significant difference exists in the fibre length (L), fibre diameter (D); fibre cell wall thickness (C) and fibre lumen diameter (I), Runkel ratio (RR), and Coefficient of flexibility (CF) at varied probability levels. However, the Slenderness ratio (SR) was not significantly ( $P > 0.05$ ) different across plant species (Table 2). The results as presented in table 3 shows that there is no significant difference between the fibre lengths of *G. arborea* and *A. boonei*, while they both differ significantly from those of *A. indica*, *P. biglobosa* and *C. siamea*. However, the fibre lengths of *A. indica*, *P. biglobosa* and *C. siamea* are statistically the same. The fibre diameter ranged from 0.0236 mm to 0.0456 mm across the different species whereby *A. boonei* recorded significantly ( $P < 0.05$ ) the widest fibre diameter (0.0456 mm  $\pm$  0.00369 mm) while *C. siamea* had the smallest fiber diameter (0.0236 mm  $\pm$  0.00097 mm) (Table 3).

TABLE 2. Analysis of variance mean square values.

Parameter	Mean square
Fibre length	1.33***
Fibre diameter	0.0010***
Fibre lumen diameter	0.0020***
Cell wall thickness	0.0000*
Runkel ratio	16.33***
Coefficient of flexibility	0.22**
Slenderness ratio	452.94 <sup>NS</sup>

\*= Significant at  $P < 0.05$ ; \*\*= Significant at  $P < 0.01$ ; \*\*\*= Significant at  $P < 0.001$ .

TABLE 3. The mean fibre lengths and diameter of the species.

Treatment	Fibre length (mm)	Fibre diameter (mm)
<i>G. arborea</i>	1.54 ± 0.90 <sup>a</sup>	0.0396 ± 0.00183 <sup>b</sup>
<i>A. boonei</i>	1.70 ± 0.08 <sup>a</sup>	0.0456 ± 0.00369 <sup>a</sup>
<i>A. indica</i>	1.15 ± 0.04 <sup>b</sup>	0.0276 ± 0.00110 <sup>c</sup>
<i>P. biglobosa</i>	1.00 ± 0.05 <sup>b</sup>	0.0240 ± 0.00143 <sup>c</sup>
<i>C. siamea</i>	1.14 ± 0.08 <sup>b</sup>	0.0236 ± 0.00097 <sup>c</sup>
F-LSD ( $P < 0.05$ )	0.198	0.0048

\*significant means are represented with different alphabets on each vertical array.

The mean fibre lumen diameters of the species are given in table 4. The result shows that there is no significant ( $P < 0.05$ ) difference between the fibre lumen diameters of *G. arborea* and *A. boonei*, but these two species differ significantly from *A. indica*, *P. biglobosa* and *C. siamea*. The fibre cell wall thickness ranged from 0.0064 mm to 0.0089 mm with *C. siamea* recording the thickest fibre which was however not significantly ( $P > 0.05$ ) different from the fibre thickness recorded by *G. arborea* and *A. boonei* (Table 4).

The mean fibre Runkel ratios of the species as presented in table 5 shows that the Runkel ratios of three species namely: *Gmelina arborea*, *Alstonia boonei* and *Azadirachta indica* are statistically the same. Nevertheless, the Runkel ratio of *Casia siamea* differed significantly from all the species. The coefficients of flexibility of *G. arborea* and *A. boonei* were similar, while they both differ significantly from those of *A. indica*, *P. biglobosa* and *C. siamea*. However,

the slenderness ratio was not significantly different across species (Table 5).

## DISCUSSION

The fibre length of *G. arborea* of 1.5 mm average observed in the present study corroborates the report of Moya, Tomazelo and Canessa (2007), therefore strengthening the reliability of our data. The result from the present study on the fibre length shows that the average fibre length (L) of *A. boonei* was 1.70 mm. In accordance with the classification of Metcalfe and Chalk (1983), fibres above 1.6 mm in length are long. Therefore, *A. boonei* has long fibres, while the fibre of other wood species studied were short. The association between fibre length and pulp and paper properties cannot be overstressed. Fibre length influences a large amount of the pulp strength properties; positive relationships have been observed between fibre length and tear index for *Pinus radiata* and *P. elliottii* (Wright and Sluis-Cremer, 1992), burst



TABLE 4. The mean fibre lumen diameters and cell wall thickness of the species

Treatment	Fibre lumen diameter (mm)	Fibre cell wall thickness (mm)
<i>G. arborea</i>	0.0266 ± 0.00203 <sup>a</sup>	0.0077 ± 0.00038 <sup>ab</sup>
<i>A. boonei</i>	0.0293 ± 0.00371 <sup>a</sup>	0.0087 ± 0.00084 <sup>a</sup>
<i>A. indica</i>	0.0122 ± 0.00103 <sup>b</sup>	0.0072 ± 0.00093 <sup>b</sup>
<i>P. biglobosa</i>	0.0098 ± 0.00109 <sup>b</sup>	0.0064 ± 0.00058 <sup>b</sup>
<i>C. siamea</i>	0.0079 ± 0.00106 <sup>b</sup>	0.0089 ± 0.00063 <sup>a</sup>
F-LSD (P < 0.05)	0.0067	0.0013

\*significant means are represented with different alphabets on each vertical array

TABLE 5. The mean fibre Runkel ratios, coefficient of flexibility and slenderness ratio of the species.

Treatment	Runkel ratios	Coefficient of flexibility	Slenderness ratio
<i>G. arborea</i>	0.624 ± 0.572 <sup>c</sup>	0.677 ± 0.045 <sup>a</sup>	40.0175 ± 3.044177
<i>A. boonei</i>	0.768 ± 0.127 <sup>c</sup>	0.643 ± 0.052 <sup>a</sup>	45.7191 ± 7.942999
<i>A. indica</i>	1.228 ± 0.107 <sup>bc</sup>	0.438 ± 0.031 <sup>b</sup>	42.5047 ± 2.197944
<i>P. biglobosa</i>	1.464 ± 0.212 <sup>b</sup>	0.458 ± 0.040 <sup>b</sup>	34.4600 ± 4.289465
<i>C. siamea</i>	3.227 ± 0.578 <sup>a</sup>	0.428 ± 0.098 <sup>b</sup>	48.8097 ± 3.483221
F-LSD (P < 0.05)	0.81	0.164	NS

\*significant means are represented with different alphabets on each vertical array.

strength (Ona *et al.* 2001), tear strength (Haygreen and Bowyer 1996) and folding endurance (Ona *et al.* 2001). Fibre length has also been shown to be principally of importance to tearing resistance (Wangaard & Williams 1970). According to Gally (1962) and Ademiluyi and Okeke (1979), greater fibre length conforms to higher tearing resistance of paper, which was attributed to stress dissipation; the longer the fibre, the larger the area over which the stress was dissipated. However, longer fibres tended to give a more open and less uniform sheet structure (Ogunleye, Fuwape, Oluyeye, Ajayi, & Fabiyi, 2017). This observation indicates that papers produced from wood fibres of *A. boonei* is likely to have high tear resistance than those from the other wood samples studied.

The fibre diameter of *G. arborea* observed in this study was higher than that reported by Moya *et al.* (2007) and Ogunkunle (2010). Okereke (1962) reported that fibre with large diameter and broad lumen diameter ensures better collapsibility and therefore provides enough bonding

surface during paper production. This implies that *A. boonei* with the largest fibre diameter will provide better inter fibre bonding while *C. siamea* will provide the least. More so, Palmer (1986) pointed out that the thinner the cell wall thickness the better the fibre for papermaking, as fibres with thin walls collapse easily and provide effective bonding surface during papermaking.

The derived fibre values are usually applied as parameters for the assessment hardwood fibres (Okereke, 1962; Ademiluyi & Okeke, 1979; Kpikpi, 1992). These values are Runkel ratio (RR), slenderness ratio (SR), and coefficient of flexibility (CF). The lower the Runkel ratio especially when it is less than 1, the better for papermaking (Dutt, Upadhyaya, Singh, & Tyagi, 2009; Ona *et al.* 2001; Ogunleye *et al.*, 2017). Based on this, *G. arborea* and *A. boonei* are considered fit for papermaking. Chittenden and Rotibi (1962) pointed out that papers made from fibre with high Runkel ratio are porous and stiff. However, fibres with relatively thin walls collapse more readily in the paper sheet

formation. This leads to strong inter-fibre bonding thus increasing the tear resistance of the paper.

The standard values for hardwood and softwoods are 0.55-0.70 and 0.75 respectively, whereby fibres having coefficient of flexibility ranging from 0.50-0.75 are considered as highly elastic fibres (Ogunleye *et al.*, 2017). This indicates the suitability of *A. boonei* as compared to *G. arborea* for papermaking. Similarly if the postulate by Ademiluyi and Okeke (1979) holds, that the higher the slenderness ratio, the greater the tear resistance of the paper, then it is reasonable to say that from our data all the tree species will show the good tear resistance as compared to *G. arborea*.

## CONCLUSIONS

The results of the investigations showed that the wood fibres of *A. boonei* and *G. arborea* among the other three species are the most suitable for papermaking. Working with the principles that the fibres with the lowest Runkel ratio and highest coefficient of flexibility make the strongest papers, the order of quality of the species studied is: *G. arborea* = *A. boonei* = *P. biglobosa* > *A. indica* > *C. siamea*. In this respect *G. arborea* is the best option for paper making followed by *A. boonei*. Since there is no significant difference between *G. arborea* and *A. boonei* in all the fiber dimensions, and using *G. arborea* as standard since it has been established as a papermaking hardwood species, it may be concluded that *A. boonei* is another pulp wood with good paper-making potentials apart from the already known *G. arborea*. Also, if fibre length is taken into consideration, *A. boonei* shows great potential as a pulping species.

## REFERENCES

- Ademiluyi, E. O. & Okeke, R. E. (1979). Studies on specific gravity and fibre characterization of *Gmelina arborea* in some Nigerian plantation. *Nigerian Journal of Science*, 13, 231-238.
- Ajuziogu, G. C., Ojua, E. O. & Aina, D. O. (2019). Comparative paper-making potentials of three species from the Verbenaceae and Lamiaceae family. *Asian Journal of Research in Botany*, 2(4), 1-5.
- Chittenden, A. E. & Rotibi, J. O. (1962). *Studies on the suitability of Nigerian raw materials for pulp making*, *Gmelina arborea*. Research Report 17, Federal Ministry of Commerce and Industry.
- Dutt, D., Upadhyaya, J. S., Singh, B., & Tyagi C. H. (2009). Studies on *Hibiscus cannabinus* and *Hibiscus sabdariffa* as an alternative pulp blend for softwood: An optimisation of kraft delignification process. *Industrial Crops and Products*, 29(1), 16-26. doi: 10.1016/j.indcrop.2008.03.005
- Egbewole, Z. T. & Rotowa, O. J. (2017). Effects of Declining Paper Industry on Nigeria Economy and the Way Forward. *American Journal of Agriculture and Forestry*, 5(6), 181-187. doi: 10.11648/j.ajaf.20170506.11
- Ervasti, I. (2016). Wood fiber contents of different materials in the paper industry material chain expressed in roundwood equivalents (RWEs). *Silva Fennica*, 50(4), 1611 - 1632. doi: 10.14214/sf.1611
- Ezeudu, O. B., Agunwamba, J. C., Ezeasor, I. C. & Madu, C. M. (2019). Sustainable production and consumption of paper and paper products in Nigeria: A review. *Resources*, 8(1), 1-23. doi: 10.3390/resources8010053
- Gallay W. (1962). In Bolam, F. (Ed.) *The formation and structure of paper*. (Technical Section of British Paper and Board Makers' Association), London, pp. 491-535.
- Keay, R. W. J., Onochie, C. F. A., & Stanfield, D. P. (1964). *Nigerian Trees* (Vol. 11). Nigeria: Federal Department of Forest Research Ibadan.
- Kpikpi, W. M. & Olatunji, A. O. (1990). Wood anatomy consideration in deciding suitability of some Nigerian hardwood for pulp and paper production. *Nigerian Journal of Botany*, 3, 137-150.
- Kpikpi, W. M. (1992). Wood structure and paper making potentials of *Recinodendron heudelottii* and *Albizia zygia* in relation to *Gmelina arborea*. *Nigerian Journal Botany*, 5, 41-50.
- Metcalf, C. R. & Chalk, L. (1989). *Anatomy of the Dicotyledons* Vol. II (2nd ed). Oxford University Press.
- Ogunkunle, A. T. J. (2010). A quantitative modelling of pulp and paper making suitability of Nigerian hardwood species. *Advances in Natural and Applied Sciences*, 4(1), 14-21.
- Ogunleye, B. M., Fuwape, J. A., Oluyeye, A. O., Ajayi, B. & Fabiyi, J. S. (2017) Evaluation of fiber characteristics of *Recinodendron heudelottii* (Baill, Pierre Ex Pax) for pulp and paper making. *International Journal of Science and Technology*, 6(1), 634-641.
- Okereke, O. O. (1962). *Studies on the fibre dimension of some Nigerian timber and other raw materials* (Part 1). Research Report 16, Federal Ministry of Commerce and Industry.



- Ona, T., Sonoda, T., Ito, K., Shibata, M., Tamai, Y., Kojima, Y., Ohshima, J., Yokota, S. & Yoshizawa, N. (2001). Investigation of relationships between cell and pulp properties in *Eucalyptus* by examination of within-tree variations. *Wood Science and Technology*, 35, 229-243. doi: 10.1007/s002260100090
- Palmer, E. R. (1973). *Gmelina arborea* as a potential source of hardwood pulp. *Tropical Science*, 15, 243-260.
- Peltola, H., Gort, J., Pulkkinen, P., Zubizarreta Gerendiain, A., Karpinen, J. & Ikonen, V-P. (2009). Differences in growth and wood density traits in Scots pine (*Pinus sylvestris* L.) genetic entries grown at different spacing and sites. *Silva Fennica*, 43(3), 339-354. doi: 10.14214/sf.192
- Picornelli, P. M. (1984): Protecting new pulp and paper industries: an opinion from developing countries. *Unasyha*, 144, 54-62.
- Moya R., R., Tomazelo F., M., & Canessa A., E. (2007). Fiber morphology in fast growth *Gmelina arborea* plantations. *Madera y Bosques*, 13(2), 3-13. doi: 10.21829/myb.2007.1321225
- Rydholm, S. A. (1967). *Pulping Process*. New York: John Wiley-Sons Ltd.
- Wangaard F. F. & Williams D. L. (1970). Fibre length and fibre strength in relation to tearing resistance of hardwood pulp. *TAPPI Journal*, 5(11), 2153-2154.
- Wright, J. A. & Sluis-Cremer, H. J. (1992). Tracheid morphology and pulp and paper strength traits of *Pinus taeda* and *P. patula* at age 17 years in South Africa. *TAPPI Journal*, 75(5), 183-187.

Received: 24 May 2019

Accepted: 21 January 2020

Published: 26 June 2020

This paper must be cited as:

Ajuziogu, G. C., Ojua, E. O., Abu, N. E., Onyeke, C. C., Ayogu, V. O., Nweze, A. E., & Nworie, S. (2020). Comparative studies of fibres of woody species selected in relation to their paper-making potentials. *Madera y Bosques*, 26(2), e2621968. doi: 10.21829/myb.2020.2621968



Madera y Bosques by Instituto de Ecología, A.C. is distributed under a Creative Commons Licence Attribution-NonCommercial-ShareAlike 4.0 Internacional.